



Fabric Bubble II

Width: 138/140 cm

Weight: 632 g/ml

Colour fastness to light: colour 0157 = 3-4**,
 colour 0123+0132+0118= 4-5**, colour 0148+0169+0142 = 4**,
 colour 0103+0101+0121+0141= 5*** - BS EN ISO 105-B02


Colour fastness to rubbing dry: colour 0132 = 4-5****, all other colours = 5**** - BS EN ISO 105-X12

Colour fastness to rubbing dry: colour 0132 = 4-5****, all other colours = 5**** - BS EN ISO 105-X12

Pilling: 4**** - EN ISO 12945-2

Composition: 52% viscose, 40% cotton, 8% flax

Abrasion: 27.000*** - EN ISO 12947-2

Cleaning instruction: 

Edge: 

Classification for upholstery to be used in privat home:

* poor ** caution *** acceptable **** good ***** very good

The fabric changes appearance depending on the angle from which it is viewed. The change can range from a more matt and darker surface to a shinier and lighter coloured one. The change is also noticeable in those areas where the fabric is exposed to wear and tear. This change is typical of velour fabrics and is an expected and intrinsic feature of this material.